


# Product Data Sheet Tensar<sup>®</sup> HX5.5-G Geocomposite

# General

The Tensar H-Series geocomposite is manufactured from an extruded, polymer sheet, which is then punched and stretched. The resulting geogrid structure consists of continuous and non-continuous ribs forming three aperture geometries (hexagon, trapezoid, and triangle) and an unimpeded suspended hexagon. A non-woven geotextile is then bonded to the geogrid to form a geocomposite.



Tensar HX5.5 Geocomposite Plan View

Tensar HX5.5 Perspective View

The Tensar H-Series geocomposite uses the distinct stabilisation function as defined in ISO 10318 to minimise the movements of unbound granular material in road, rail and other trafficked areas. Extensive performance testing has demonstrated that when included as a component of a mechanically stabilised layer, the mechanical behaviour of the unbound layer is improved. The characteristics below allow product identification only.

## Identification Properties (1)

## Geogrid component

- Aperture shapes
- Structure
- Rib shape
- Continuous parallel rib pitch
- Rib aspect ratio<sup>(2)</sup>
  Node thickness
  Colour identification

# Geotextile component

- Static puncture resistance<sup>(3)</sup>
- Dynamic perforation resistance<sup>(4)</sup>
- Characteristic opening size<sup>(5)</sup>
- Water permeability normal to the plane (Velocity 0.11m/s (Tolerance -0.05m/s) Index)<sup>(6)</sup>

# General

Hexagonal,Trapezoidal,&Triangular Integrally Formed Rectangular 80mm > 1.0 3.0mm Black

1.30kN (Tolerance -0.5kN) 35mm (Tolerance +10mm) 140µm (Tolerance ±60µm) 0.11m/s (Tolerance -0.05m/s)



#### **Dimensions and delivery**

The geocomposite shall be delivered in roll form with each roll individually identified as Tensar HX5.5-G geocomposite. Roll dimensions are typically 50m long by 3.8m wide.

#### Notes

- 1. Unless noted otherwise, the values shown are nominal
- 2. Ratio of the mid-rib depth to the mid-rib width
- 3. Measured in accordance with EN ISO 12236
- 4. Measured in accordance with EN ISO 13433
- 5. Measured in accordance with EN ISO 12956
- 6. Measured in accordance with EN ISO 11058

The information in this document supersedes any previous bulletins in relation to this subject matter and is supplied by Tenar International Limited free of charge for general information purposes only. This document does not form part of any contract or intended contract. Tensar International Limited excludes to the fullest extent lawfully permitted any and all liability whatsoever for any loss or damage howsoever arising out of the use of and relance upon this information. It is your sole responsibility, and you must assume all risk and liability for the final determination as to the suitability of any Tensar International Limited product and/or design for the use and in the manner contemplated by you in connection with a particular project.

#### **Registered Office**

Units 2-4 Cunningham Court, Shadsworth Business Park Blackburn, Lancashire, BB1 2QX, UK

Tensar is a Division of CMC Tensar, InterAx, H-Series and TriAx are registered trademarks Copyright © Tensar International Limited 2024





4001:2015

uring Ltd